

Binder **PG 70-28**
Temp (F) Viscosity (cp)
275 **788**
329 **225**

Mixing Temperature Range, F 338 - 350
Compaction Temperature Range, F 314 - 324

Specific Gravity @ 60F **1.0377**



CAUTION: Mixing Temperature may exceed 177C (350F). Recommend consulting with asphalt binder supplier.

