

Binder **PG 64-28 ER**
Temp (F) Viscosity (cp)
275 850
329 230

Mixing Temperature Range, F 338 - 351
Compaction Temperature Range, F 315 - 325

Specific Gravity 60F **1.0377**

CAUTION: Mixing Temperature may exceed 177C (350F). Recommend consulting with asphalt binder supplier.

