

Binder **PG 70-22 ER**
Temp (F) Viscosity (cp)
275 863
329 238

Mixing Temperature Range, F 340 - 353
Compaction Temperature Range, F 317 - 327

Specific Gravity@60F **1.034**



CAUTION: Mixing Temperature may exceed 177C (350F). Recommend consulting with asphalt binder supplier.

