


Binder **PG 70-28 ER**
 Temp (F) Viscosity (cp)
 275 938
 329 250

Mixing Temperature Range, F 342 - 355
 Compaction Temperature Range, F 319 - 329

Specific Gravity 60F **1.0377**



CAUTION: Mixing Temperature may exceed 177C (350F). Recommend consulting with asphalt binder supplier.

