

Binder **PG 58-22**
Temp (F) Viscosity (cp)
275 **363**
329 **129**

Mixing Temperature Range, F 307 - 320
Compaction Temperature Range, F 282 - 293

Specific Gravity@ 60F **1.0319**

