

Binder **PG 64-22**
Temp (F) Viscosity (cp)
275 **438**
329 **121**

Mixing Temperature Range, F 308 - 319
Compaction Temperature Range, F 288 - 297

Specific Gravity@ 60F **1.0294**

