

Binder **PG 64-28**  
Temp (F) Viscosity (cp)  
**275** **446**  
**329** **129**

Mixing Temperature Range, F 310 - 322  
Compaction Temperature Range, F 289 - 298

Specific Gravity@ 60F **1.035**

