

Binder **PG 70-22**  
Temp (F) Viscosity (cp)  
**275** **638**  
**329** **188**

Mixing Temperature Range, F 328 - 341  
Compaction Temperature Range, F 305 - 315

Specific Gravity@60F **1.0454**

